

TECHNICAL PRODUCT INFORMATION

Product:	Black/White film
Catalog Number:	E1115
Durability:	10-12 months at 160-180Kly
Thickness:	20-50 μ
Width:	0.5-14.0 m
Length:	According to customer order

Product properties

Property	Test Method	Units	Value
Tensile Strength at break [MD]	ASTM D-882	MPa.	26
Tensile Strength at break [TD]	ASTM D-882	MPa.	26
Elongation at break [MD]	ASTM D-882	%	400
Elongation at break [TD]	ASTM D-882	%	600
Falling Dart Impact	ASTM D-1709	gr.	500
Total light transmission	EN 2155	%	Max 1%
Thickness average	EN 13206	%	$\pm 5\%$ on nominal
Thickness tolerance	EN 13206	%	$\pm 15\%$

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required