

TECHNICAL PRODUCT INFORMATION

Product:	Stabilized Black film
Catalog Number:	E1131
Durability:	30 microns- 2 Seasons at 120KLy 50 microns- 3 Seasons at 120 Kly 100 microns- 4 years at 120 Kly
Thickness:	30-200 microns
Width:	Up to 18.0 m
Length:	According to customer order

Product properties

Property	Test Method	Units	Value
Tensile Strength at break [MD]	ASTM D-882	MPa.	22
Tensile Strength at break [TD]	ASTM D-882	MPa.	22
Elongation at break [MD]	ASTM D-882	%	400
Elongation at break [TD]	ASTM D-882	%	600
Falling Dart Impact	ASTM D-1709	gr.	150
Total light transmission		%	Max 1%
Thickness average		%	±5% on nominal
Thickness tolerance		%	±15%

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required