

## TECHNICAL PRODUCT INFORMATION

Product:	Thermic Solarization film with anti-drip
Catalog Number:	E1313
UV resistance:	4 months
Thickness:	15-50 $\mu$ depend on the width
Width:	Up to 11 m
Length:	According to customer order

### Product properties

Property	Test Method	Units	Value
Tensile Strength at break[MD]	ASTM D-882	MPa.	25
Tensile Strength at break[TD]	ASTM D-882	MPa.	23
Elongation at break [MD]	ASTM D-882	%	500
Elongation at break [TD]	ASTM D-882	%	500
Falling Dart Impact	ASTM D-1709	gr.	250
Total light transmission	EN 13206	%	90
Thickness average	EN 13206	%	$\pm 5\%$ on nominal
Thickness tolerance	EN 13206	%	$\pm 15\%$

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required