

## TECHNICAL PRODUCT INFORMATION

Product:	Diffused stabilized film
Catalog Number:	E2358
Product description:	UVA DIFFUSED. The light diffusion reduces construction and self shadows and allows the plants to receive a more even distribution of light during the day. By eliminating shadows and spreading available energy more evenly on the leaf surface there is less stress on the top canopy of the plant and more photosynthesis occurring in the lower canopy.
Durability:	2 years at 160-180 Kly 3 years at 120 Kly
Thickness:	150-300 $\mu$
Width:	1.0-14.5 m
Length:	According to customer order

Property	Test Method	Units	Value
Tensile Strength at break[MD]	ASTM D-882	MPa.	27
Tensile Strength at break[TD]	ASTM D-882	MPa.	27
Elongation at break [MD]	ASTM D-882	%	500 min
Elongation at break [TD]	ASTM D-882	%	500 min
Tear resistance[MD]	ASTM D-1922	Kg./mm	9.0
Tear resistance[TD]	ASTM D-1922	Kg./mm	11.0
Falling Dart Impact	ASTM D-1709	gr.	1000
Total light transmission at 400-700 nm	EN13206	%	85
Light diffusion at 400-700 nm	EN13206	%	65
Thermicity	EN13206	%	50
UV irradiation transmission at 250-400 nm	EN13206	%/nm	98/350
Thickness average	EN13206	%	$\pm 5\%$ on nominal
Thickness tolerance	EN13206	%	$\pm 15\%$

## **Use and limitation:**

- **Exposure to chemicals:** exposure of greenhouse films to severe chemical conditions has an adverse effect on the lifetime of the film. Avoid excessive use of agrochemicals such as pesticides, herbicides, fungicides and fertilizers. Take measures to prevent direct contact of chemicals to the film. Ensure that metal structures are galvanized and are free from corrosion. When wooden structure parts are used, avoid contact of the film with resin, oil, petroleum or volatile preservatives. Prevent contact of the film with PVC accessories. Chemicals containing halogens, sulfur, copper, iron, are known to accelerate the degradation of greenhouse films.

**Specifically, if the following elements are found at levels higher than specified, the films are excluded from this warranty:**

**Sulfur: max 100 ppm, Chlorine: 10 ppm, Iron: 50 ppm**

- **Overheating** the film has an adverse effect on its lifetime. Hot air should be directed away from the film.
- When gases are used to disinfect the soil, the treated soil must be covered with a film for a minimum of three weeks. After the film is removed, the greenhouse should be ventilated.