

TECHNICAL PRODUCT INFORMATION

| | |
|----------------------|--|
| Product: | Diffused thermic UV stabilized film |
| Catalog Number: | E2465 |
| Product description: | Diffused thermic multi-layer greenhouse cover. The film contains light diffusers to allows the plants to receive a more even distribution of light during the day, thermic (IR) ingredients reduce heat loss at night. |
| Durability: | 3 years |
| Thickness: | 150-300 μ |
| Width: | Up to 18.0 m |
| Length: | According to customer order |

Product properties

| Property | Test Method | Units | Value |
|-----------------------------------|-------------|--------|----------------------|
| Tensile Strength at break [MD] | ASTM D-882 | MPa. | 27 |
| Tensile Strength at break [TD] | ASTM D-882 | MPa. | 27 |
| Elongation at break [MD] | ASTM D-882 | % | 800 min |
| Elongation at break [TD] | ASTM D-882 | % | 800 min |
| Tear resistance [MD] | ASTM D-1922 | Kg./mm | 9.0 |
| Tear resistance [TD] | ASTM D-1922 | Kg./mm | 10.0 |
| Falling Dart Impact (200 microns) | ASTM D-1709 | gr. | 1200 |
| Total light transmission | ASTM 1003 | % | >89 |
| Light diffusion (Haze) | ASTM 1003 | % | >90 |
| Thermicity | EN 13206 | % | 85 |
| UV transmission at 250-380 nm | EN 13206 | % | N.A. |
| Thickness average tolerance | EN 13206 | % | $\pm 5\%$ on nominal |

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required

Use and limitation:

- **Exposure to chemicals:** exposure of greenhouse films to severe chemical conditions has an adverse effect on the lifetime of the film. Avoid excessive use of agrochemicals such as pesticides, herbicides, fungicides and fertilizers. Take measures to prevent direct contact of chemicals to the film. Ensure that metal structures are galvanized and are free from corrosion. When wooden structure parts are used, avoid contact of the film with resin, oil, petroleum or volatile preservatives. Prevent contact of the film with PVC accessories. Chemicals containing halogens, sulfur, copper, iron, are known to accelerate the degradation of greenhouse films.

Specifically, if the following elements are found at levels higher than specified, the films are excluded from this warranty:

Sulfur: max 1500 ppm, Chlorine: 100 ppm, Iron: 50 ppm

- **Overheating:** the film has an adverse effect on its lifetime. Hot air should be directed away from the film.
- **Disinfection chemical use:** when chemicals are used to disinfect the soil, the treated soil must be covered with a film for a minimum of three weeks. After the film is removed, the greenhouse should be ventilated.

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required